

AMENDMENTS TO THE SPECIFICATION:

Please amend the specification as follows:

Page 22, replace Table 1 with the following amended Table 1.

Table 1

	Unit	Ex. 1	Ex. 2	Comp. Ex. 1	Comp. Ex. 2	Comp. Ex. 3
Polyphenylene ether: a-1	%	71.4	71.4	71.4	71.4	71.4
Thermoplastic elastomer: b-1 b-2 b-3	%			5.5	5.5	5.5 5.5
Inorganic filler: c-1 c-2 c-3	%				22.0	
BHT	%	1.1	1.1	1.1	1.1	1.1
Aromatic phosphoric ester based flame retarder: d-1	Part	11.0	11.0	11.0	11.0	11.0
Drop impact strength	J	44	40	14	10	35
IZOD impact value	J/m	108	98	39	59	59
Flexural modulus	MPa	3800	3700	3800	3700	3750
Elongation at break	%	100<	80	8	18	22
Gloss	%	88	80	50	48	72

Page 25, replace Table 2 with the following amended Table 2.

Table 2

	Unit	Comp. Ex. 4	Ex. 3	Ex. 4	Comp. Ex. 5	Comp. Ex. 6
Polyphenylene ether:	%					
a-1		71.4	71.4 ^(*)	32.7	32.7	32.7
Polystyrene:				35.6	35.6	35.6
a-2						
Thermoplastic elastomer:	%				5.9	
b-1						
b-2						
b-3		5.5	5.5	5.9		21.9
Inorganic filler:	%					
c-1						
c-2			22.0	24.8	24.8	24.8
c-3				24.8	24.8	24.8
BHT	%	1.1	1.1	1.1	1.1	1.1
Aromatic phosphoric ester based flame retarder:	Part					
d-1		11.0	11.0			
Drop impact strength	J	42	45	43	4	8
IZOD impact value	J/m	39	104			
Flexural modulus	MPa	2500	3750	4300	4200	2400
Elongation at break	%	19	100<			
Gloss	%	94	88	84	44	52

*1: 38.5% of 71.4% was fed from the feed port on the side surface of the extruder.